

CHEMICKÉ ODOLNOSTI / CHEMICAL RESISTANT

Chemikálie	EP 01	EP01 EKO	EP 02	EP02 EKO	EP 11	EP 12	EP 21	EP 31	EP 41	TOPSTONE FILLER	PLAST BETON	Chemicals
Amoniak 10%	A	A	A	A	A	A	A	A	B	A	A	Ammonia 10%
Styren	C	C	C	C	C	C	C	C	A	C	C	Styrene
Kyselina dusičná 10%	B	B	B	B	A	A	B	A		B	B	Nitric Acid 10%
Kyselina chlorovodíková 37%	C	C	C	C	B	B	C	B	B	C	C	Hydrochloric acid 37%
Kyselina chlorovodíková 10%	A	A	A	A	A	A	A	A	B	A	A	Hydrochloric acid 10%
Kyselina octová 10%	B	B	C	C	B	B	B	B	A	C	B	Acetic acid 10%
Kyselina fosforečná 10%	C	C	C	C	B	B	C	B	C	C	C	Phosphoric acid 10%
Kyselina sírová 50%	A	A	A	A	A	A	A	A	A	A	A	Sulphuric acid 50%
Kyselina sírová 10%	B	B	B	B	A	A	B	A	A	B	B	Sulphuric acid 10%
Kyselina mléčná 10%	A	A	B	B	A	A	A	A	A	B	A	lactic acid 10%
Hydroxid sodný 10%	A	A	A	A	A	A	A	A	A	A	A	Sodium Hydroxide 10%
Nitro rozpouštědlo	D	D	D	D	D	D	D	D	-	D	C	Nitro solvent
Xylen	A	A	A	A	A	A	A	A	A	A	A	Xilene
MIBK	B	B	A	A	B	B	B	B	-	A	B	MIBK
Butylacetát	C	C	C	C	C	C	C	C	A	C	C	Butyl acetate
Ethanol 95%	C	C	C	C	C	C	C	C	B	C	C	Ethanol 95%
Chlornan sodný	A	A	A	A	A	A	A	A	A	A	A	Sodium Hypochlorite 5,5%
Voda destilovaná	A	A	A	A	A	A	A	A	A	A	A	H2O distilled
Voda deionizovaná	A	A	A	A	A	A	A	A	A	A	A	Water deionized
Voda mořská	A	A	A	A	A	A	A	A	A	A	A	Sea water
Voda odpadní	A	A	A	A	A	A	A	A	A	A	A	Waste water
Voda pitná	A	A	A	A	A	A	A	A	A	A	A	Potable water
Nafta	A	A	A	A	A	A	A	A	A	A	A	OIL
Benzin	A	A	A	A	A	A	A	A	A	A	A	Petrol
Posypová sůl	A	A	A	A	A	A	A	A	A	A	A	Road salt

Legenda / Legend:

- A trvalá odolnost / permanent resistant
- B dlouhodobá odolnost / longtime resistant
- C krátkodobá odolnost / shorttime resistant
- D neodolné / not resistant